

General Instructions

- 1** Clean surfaces with alcohol or compatible solvent.
- 2** Lightly sand any glossy surfaces.
- 3** Apply an even coat to both surfaces to be joined.
- 4** Allow cement to set for 10-30 minutes or until tacky.
- 5** Press together and allow to bind before use.

Use our RH Thinner for prep and cleanup.

Technical Data

Base: Neoprene Resin

Solvent: Toluene, Heptane, Ethyl Acetate, Acetone

Color: Amber Clear

Viscosity: Medium, 1550-1750 cps at room temperature

Application: Brush, Roller, Notched Trowel, Squeeze Bottle

Solids: 20% ± 1% (approx.)

Net Weight: 7.2 lbs./gallon (approx.)

Temperature Range: -30° to 150° F

Flash Point: 18° F

Shelf Life: 18 months from date of manufacture

Tack Time: 10 to 30 minutes

Coverage: 1 oz./sq. ft. (bonded area)

